

PRODUCT INFORMATION

Norm	EN ISO 26986			
Intensity of use	ISO 10874 (EN 685)		22 domestic general	class
Total thickness	EN ISO 24346 (EN 428)		2,80	mm
Wear layer	EN ISO 24340 (EN 429)		0,20	mm
Abrasion group	EN 660-2		T	class
Total weight	EN ISO 23997 (EN 430)		1600	g/m ²

TECHNICAL INFORMATION

Dimensional stability	EN ISO 23999 (EN 434)		≤ 0,40	%
Curling	EN ISO 23999		≤ 8	mm
Light stability	EN ISO 105 B02		≥ 6	degree
Residual indentation	EN ISO 24343-1 (EN 433)		≤ 0,35	mm
Impact sound improvement	EN ISO 717/2		Δ Lw 16	dB
Dynamic coefficient of friction	EN 13893		> 0,60	
Slip resistance (ramp test with oil)	DIN 51130		R10	scale
Reaction to fire Report number ---- VNLf 031380.4	EN 13501-1		Bfl-s1	class
Underfloor heating	EN 12667		suitable	
Thermal resistance	ISO 8302		0,025	m ² .K/W
Thermal conductivity	EN 12524		0,10	W/(m.K)
Chemical resistance	ISO 26987 (EN 423)		resistant	
Static electrical propensity	EN 1815		< 2kV	on concrete
Pendulum test	CENTS 15676:2007		40+	
Cold welding	Werner Müller		type A	

FEATURES







- No heavy metals
- No solvents
- No Formaldehydes
- No harmful plasticizers







100% phthalate free

Ortho-phthalates free